VALOX™ RESIN V2000DM

REGION ASIA

DESCRIPTION

Unreinforced, directly metallizable PBT injection molding resin with high flow better release characteristics.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	59	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	40	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	20	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D 638
Tensile Modulus, 5 mm/min	2800	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2570	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	59	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	15	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, -30°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	46	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	54	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	2	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	4	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	185	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	54	°C	ASTM D 648
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	8.4E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	186	°C	ISO 306
Vicat Softening Temp, Rate B/120	185	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	53	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.32	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	2.1 – 2.4	%	SABIC method
Melt Flow Rate, 250°C/2.16 kgf	35.4	g/10 min	ASTM D 1238

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.32	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.34	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
Melt Volume Rate, MVR at 250°C/2.16 kg	34	cm³/10 min	ISO 1133
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	12	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	245 – 260	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	50 – 75	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 100	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.013 – 0.025	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved