

LEXANTM RESIN VR2220

REGION AMERICAS

DESCRIPTION

Mid-flow, UV stabilized polycarbonate resin with mold release. Available in limited transparent tints, limited package types, and must meet minimum order quantity requirements

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	63	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D 638
Tensile Modulus, 5 mm/min	2350	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2300	MPa	ASTM D 790
Hardness, Rockwell M	70	-	ASTM D 785
Hardness, Rockwell R	120	-	ASTM D 785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D 1044
Tensile Stress, yield, 50 mm/min	63	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	110	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2300	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	800	J/m	ASTM D 256
Izod Impact, notched, -30°C	N/A	J/m	ASTM D 256
Tensile Impact Strength, Type S	546	kJ/m ²	ASTM D 1822
Falling Dart Impact (D 3029), 23°C	169	J	ASTM D 3029
Instrumented Impact Total Energy, 23°C	64	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	12	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	35	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	154	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	127	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	138	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E 831
CTE, -40°C to 95°C, xflow	6.84E-05	1/°C	ASTM E 831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Specific Heat	1.26	J/g·°C	ASTM C 351
Thermal Conductivity	0.19	W/m·°C	ASTM C177
CTE, 23°C to 80°C, flow	7.E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	142	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	136	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	125	°C	ISO 75/Ae
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm³/g	ASTM D 792
Density	1.19	g/cm³	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570
Water Absorption, equilibrium, 23C	0.35	%	ASTM D 570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D 570
Mold Shrinkage on Tensile Bar, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10.5	g/10 min	ASTM D 1238
Density	1.2	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	12	cm³/10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	88	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003
Refractive Index	1.586	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>1.E+17	Ohm-cm	ASTM D 257
Dielectric Strength, in air, 3.2 mm	15	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D 150
Relative Permittivity, 1 MHz	2.96	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D 150
Dissipation Factor, 1 MHz	0.01	-	ASTM D 150
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-221022	-	-
UL Recognized, 94HB Flame Class Rating	0.76	mm	UL 94

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Oxygen Index (LOI)	25	%	ASTM D 2863
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.