

# LEXAN<sup>TM</sup> FR RESINS ML5411H

REGION AMERICAS

## DESCRIPTION

LEXAN ML5411H Polycarbonate (PC) is an injection moldable grade that is 9% glass fiber filled. It has a UL94 V2@1.47mm rating.

## TYPICAL PROPERTY VALUES

Revision 20191031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	60	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	48	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	99	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3100	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	106	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	135	°C	ASTM D 648
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.27	-	ASTM D 792
Water Absorption, 24 hours	0.15	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
<b>FLAME CHARACTERISTICS</b>			
UL Recognized, 94V-2 Flame Class Rating	1.47	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.