LNP™ THERMOTUF™ COMPOUND VF003

VF-1003
REGION ASIA

DESCRIPTION

LNP THERMOTUF VF003 is a compound based on Super Touch Nylon resin containing 15% Glass Fiber. Added features of this material include: High Impact.

TYPICAL PROPERTY VALUES

Revision 20190411

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	77	MPa	ASTM D 638
Tensile Strain, break	2.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	5010	MPa	ASTM D 638
Flexural Stress	124	MPa	ASTM D 790
Flexural Modulus	4480	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	608	J/m	ASTM D 4812
Izod Impact, notched, 23°C	90	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	241	°C	ASTM D 648
Relative Temp Index, Elec (1)	65	°C	UL 746B
Relative Temp Index, Mech w/impact (1)	65	°C	UL 746B
Relative Temp Index, Mech w/o impact (1)	65	°C	UL 746B
PHYSICAL			
Density	1.23	g/cm³	ASTM D 792
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	0	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E207780-103093687	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved

CHEMISTRY THAT MATTERS™