LNP™ COLORCOMP™ COMPOUND 61000EUI

REGION ASIA

DESCRIPTION

LNP* COLORCOMP* 61000EUI is an unreinforced compound based on PBT+PC Alloy. Added features of this grade include: Impact Modified, improved retention of mechanical properties under UV exposure and excellent low temperature impact and chemical resistance.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	53	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	51	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	120	%	ASTM D 638
Tensile Modulus, 50 mm/min	2250	MPa	ASTM D 638
Tensile Modulus, 5 mm/min	2250	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	84	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2030	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	50	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4	%	ISO 527
Tensile Strain, break, 50 mm/min	120	%	ISO 527
Tensile Modulus, 1 mm/min	2050	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2000	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	710	J/m	ASTM D 256
Izod Impact, notched, -30°C	530	J/m	ASTM D 256
Izod Impact, notched, -40°C	299	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	60	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	50	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	30	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	55	kJ/m²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	122	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	84	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	107	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	99	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	9.5E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.5E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	120	°C	ISO 306
Vicat Softening Temp, Rate B/120	125	°C	ISO 306

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	75	°C	ISO 75/Af
Relative Temp Index, Elec [1]	75	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	75	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	75	°C	UL 746B
PHYSICAL			
Specific Gravity	1.21	-	ASTM D 792
Specific Volume	0.83	cm³/g	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.8 – 1	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.8 – 1	%	SABIC method
Density	1.22	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Flow Rate, 250°C/5.0 kg	16	g/10 min	ISO 1133
Melt Volume Rate, MVR at 250°C/5.0 kg	15	cm³/10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	1	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	0	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E207780-103938363	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
UV-light, water exposure/immersion	F2	-	UL 746C
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	.02	%	
Melt Temperature	260 – 275	°C	
Nozzle Temperature	255 – 270	°C	
Front - Zone 3 Temperature	255 – 275	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	245 – 265	°C	
Mold Temperature	65 – 90	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	50 – 80	rpm	
Shot to Cylinder Size	50 – 80	%	
Vent Depth	0.013 – 0.02	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

© 2019 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved