LNP™ COLORCOMP™ COMPOUND G1000

G-1000
REGION EUROPE

DESCRIPTION

LNP COLORCOMP G1000 is an unfilled Polysulfone resin. Added feature of this grade is: Transparent.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 50 mm/min	76	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.9	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	115	MPa	ISO 178
Flexural Modulus, 2 mm/min	2500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	6.1E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	6.2E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	183	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	170	°C	ISO 75/Af
Relative Temp Index, Elec	160	°C	UL 746B
Relative Temp Index, Mech w/impact	140	°C	UL 746B
Relative Temp Index, Mech w/o impact	150	°C	UL 746B
PHYSICAL			
Mold Shrinkage, flow	0.4 – 0.7	%	SABIC method
Density	1.24	g/cm³	ISO 1183
Water Absorption, 23°C/24hrs	0.4	%	ISO 62-1
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥4.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥6	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥1.5	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E45329-104098070	-	-
UL Recognized, 94V-0 Flame Class Rating	≥4.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	360 – 370	°C	
Front - Zone 3 Temperature	350 – 360	°C	
Middle - Zone 2 Temperature	340 – 350	°C	
Rear - Zone 1 Temperature	325 – 340	°C	
Mold Temperature	150	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved