LNP™ THERMOCOMP™ COMPOUND AF004AH

AF-1004

DESCRIPTION

LNP THERMOCOMP* AF004AH is a compound based on ABS resin containing 20% Glass Fiber. Added feature of this material is: Healthcare.

TYPICAL PROPERTY VALUES

Revision 20191218

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	70	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.2	%	ASTM D 638
Tensile Modulus, 5 mm/min	6170	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	130	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6150	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	81	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	6000	MPa	ISO 527
Flexural Stress	123	MPa	ISO 178
Flexural Modulus, 2 mm/min	5860	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	395	J/m	ASTM D 4812
Izod Impact, notched, 23°C	80	J/m	ASTM D 256
Multiaxial Impact	3	J	ISO 6603
Instrumented Impact Total Energy, 23°C	11	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	23	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	103	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	93	°C	ISO 75/Af
PHYSICAL			
Density	1.19	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.24	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.24	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.4	%	ISO 294
Density	1.19	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.39	%	ISO 62
FLAME CHARACTERISTICS			
UL Recognized, 94HB Flame Class Rating	1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Maximum Moisture Content	0.05 – 0.1	%	
Melt Temperature	260	°C	
Front - Zone 3 Temperature	265 – 275	°C	
Middle - Zone 2 Temperature	230 – 245	°C	
Rear - Zone 1 Temperature	205 – 215	°C	
Mold Temperature	70 – 80	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved