LNP™ THERMOCOMP™ COMPOUND D251RC

DESCRIPTION

LNP* Thermocomp* D251RC (experimental grade name as EXTC8483) is a compound based on Recycle Polycarbonate resin containing Glass Fiber, Flame Retardant. Added features of this material include: high modulus, good flatness, good ductility, Non-Brominated & Non-Chlorinated Flame Retardant. Post-Consumer Recycling (PCR) polycarbonate content up to 35%.

TYPICAL PROPERTY VALUES

Revision 20191217

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Flexural Modulus, 1.3 mm/min, 50 mm span	6050	MPa	ASTM D 790
Flexural Stress, yld, 1.3 mm/min, 50 mm span	161	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	158	MPa	ASTM D 790
Flexural Modulus, 2 mm/min	6150	MPa	ISO 178
Flexural Stress, yield, 2 mm/min	161	MPa	ISO 178
Flexural Stress, break, 2 mm/min	160	MPa	ISO 178
Tensile Modulus, 5 mm/min	6700	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	109	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.6	%	ASTM D 638
Tensile Modulus, 1 mm/min	6650	MPa	ISO 527
Tensile Stress, break, 5 mm/min	107	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.6	%	ISO 527
IMPACT			
Izod Impact, notched, 23°C	140	J/m	ASTM D 256
Izod Impact, notched, -30°C	90	J/m	ASTM D 256
Izod Impact, unnotched, 23°C	680	J/m	ASTM D 4812
Izod Impact, notched 80*10*4 +23°C	13	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m²	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	41	kJ/m²	ISO 180/1U
Instrumented Impact Total Energy, 23°C	22	J	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	115	°C	ASTM D 648
HDT, 0.45 MPa, 3.2 mm, unannealed	120	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	121	°C	ISO 75/Bf
Vicat Softening Temp, Rate B/50	122	°C	ISO 306
Vicat Softening Temp, Rate B/120	125	°C	ISO 306
CTE, 23°C to 80°C, flow	2.6E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, xflow	7.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.5E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.3E-05	1/°C	ASTM E 831
Relative Temp Index, Elec [1]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	80	°C	UL 746B

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Density	1.35	g/cm³	ASTM D 792
Melt Flow Rate, 300°C/2.16 kgf	25	g/10 min	ASTM D 1238
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 300°C/2.16 kg	21	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm³/10 min	ISO 1133
Mold Shrinkage, flow, 24 hrs	0.2 – 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.2 – 0.4	%	ASTM D 955
Water Absorption, 23°C/24hrs	0.03	%	ISO 62-1
ELECTRICAL			
Dielectric Constant, 1.1 GHz	3.25	-	SABIC method
Dielectric Constant, 1.9 GHz	3.26	-	SABIC method
Dielectric Constant, 5 GHz	3.26	-	SABIC method
Dielectric Constant, 10 GHz	3.26	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0068	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0069	-	SABIC method
Dissipation Factor, 5 GHz	0.0071	-	SABIC method
Dissipation Factor, 10 GHz	0.0073	-	SABIC method
Surface Resistivity	>1.0E+16	Ohm	ASTM D 257
Volume Resistivity	>1.0E+16	Ohm-cm	ASTM D 257
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E207780-103127360	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.6	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥0.5	mm	UL 94
Glow Wire Ignitability Temperature, 2.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.6 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.6 mm	960	°C	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	3 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

© 2019 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved