LNP™ THERMOCOMP™ COMPOUND LC006EX1

REGION ASIA

DESCRIPTION

LNP™ THERMOCOMP™ LC006EX1 is a special compound based on Polyetheretherketone resin containing 30% Carbon Fiber. Added features of this material include: High modulus, high impact, easy molding, electrical conductive.

TYPICAL PROPERTY VALUES

Revision 20191212

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	276	MPa	ASTM D 638
Tensile Strain, break	1.74	%	ASTM D 638
Tensile Modulus, 5 mm/min	26500	MPa	ASTM D 638
Flexural Stress	398	MPa	ASTM D 790
Flexural modulus	21300	MPa	ASTM D 790
Tensile Stress, break	267.5	MPa	ISO 527
Tensile Strain, break	1.5	%	ISO 527
Tensile Modulus, 1 mm/min	29187	MPa	ISO 527
Flexural Stress	412	MPa	ISO 178
Flexural Modulus	25395	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	860	J/m	ASTM D 4812
Izod Impact, notched, 23°C	97.3	J/m	ASTM D 256
Multiaxial Impact	8.42	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	55.6	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9.85	kJ/m²	ISO 180/1A
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	55	kJ/m²	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	8.1	kJ/m²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	338	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	329	°C	ASTM D 648
CTE, -40°C to 120°C, flow	9.3E-06	1/°C	ASTM E 831
CTE, -40°C to 120°C, xflow	3.4E-05	1/°C	ASTM E 831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	337	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	322	°C	ISO 75/Af
PHYSICAL			
Moisture Absorption, 50% RH, 24 hrs	0.052	%	ASTM D 570
Specific Gravity	1.423	-	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.28	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.1	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.072	%	ISO 62
Density	1.42	g/cm³	ASTM D 792
INJECTION MOLDING			
Drying Temperature	150	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4 – 6	hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved