LNP™ THERMOCOMP™ COMPOUND LC008EXQ

LC008EXQ

DESCRIPTION

LNP THERMOCOMP LC008EXQ is a compound based on Polyetheretherketone containing 40% Carbon Fiber. Added features of this grade include: Electrically Conductive, Easy Molding.

TYPICAL PROPERTY VALUES

Revision 20191213

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	330	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	41480	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	492	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	35200	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	321	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.4	%	ISO 527
Tensile Modulus, 1 mm/min	40420	MPa	ISO 527
Flexural Stress	460	MPa	ISO 178
Flexural Modulus, 2 mm/min	33820	MPa	ISO 178
Compressive Strength	215	MPa	SABIC method
Shear Modulus	5003	MPa	ASTM D732
Shear Strength	126	MPa	ASTM D732
IMPACT			
Izod Impact, unnotched, 23°C	863	J/m	ASTM D 4812
Izod Impact, notched, 23°C	82	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	7	J	ASTM D 3763
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	335	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.44	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.15 – 0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.7 – 1.4	%	ASTM D 955
Poisson's Ratio	0.47	-	ASTM E 132
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+03	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved