LNP™ THERMOCOMP™ COMPOUND MX00709

MF-1004 HS UV HP

DESCRIPTION

LNP THERMOCOMP MX00709 is a compound based on Polypropylene resin containing 20% Glass Fiber. Added features of this grade are: Heat Stabilized, UV Stabilized.

TYPICAL PROPERTY VALUES

Revision 20191213

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	76	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	7860	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	123	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	6170	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	103	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	151	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.15	-	ASTM D 792
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	225 – 250	°C	
Front - Zone 3 Temperature	240 – 250	°C	
Middle - Zone 2 Temperature	215 – 225	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	30 – 50	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved