LNP™ THERMOCOMP™ COMPOUND RF0069SZ

RF-1006 FR-1 HS
REGION ASIA

DESCRIPTION

LNP THERMOCOMP RF0069SZ is a compound based on Nylon 66 resin containing 30% Glass Fiber. Added features of th is grade include: Flame Retardant, Heat Stabilized.

TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	161	MPa	ASTM D 638
Tensile Strain, break	1.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	13350	MPa	ASTM D 638
Flexural Stress	220	MPa	ASTM D 790
Flexural modulus	11230	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	600	J/m	ASTM D 4812
Izod Impact, notched, 23°C	55	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	233	°C	ASTM D 648
Relative Temp Index, Elec [1]	130	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	105	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	115	°C	UL 746B
PHYSICAL			
Density	1.65	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.3	%	ASTM D 955
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 0	≥1.7	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥1.7	mm	UL 746A
High Voltage Arc Track Rate {PLC}	1	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D 495
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E207780-101281608	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.75	mm	UL 94

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

© 2019 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved