LNP™ THERMOCOMP™ COMPOUND WB006

WB-1006
REGION AMERICAS

DESCRIPTION

LNP THERMOCOMP WB006 is a compound based on Polybutylene Terephalate resin containing Glass Bead.

TYPICAL PROPERTY VALUES

Revision 20191108

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	54	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.2	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	5.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	4070	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	78	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3980	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	54	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	3.7	%	ISO 527
Tensile Strain, break, 5 mm/min	4.4	%	ISO 527
Tensile Modulus, 1 mm/min	4200	MPa	ISO 527
Flexural Modulus, 2 mm/min	3600	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	172	J/m	ASTM D 4812
Izod Impact, notched, 23°C	22	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	4	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	11	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	2	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	186	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	106	°C	ASTM D 648
CTE, -30°C to 30°C, flow	7.4E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.1E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	170	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	93	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.57	-	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	1 – 4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1 – 4	%	ASTM D 955
Density	1.54	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.06	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	240 – 265	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	220 – 230	°C	
Mold Temperature	80 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved