LNP™ THERMOCOMP™ COMPOUND ZKC06

DESCRIPTION

LNP* Thermocomp* ZKC06 is a compound based on PPO resin containing Mineral Filler, Impact Modifier. Added features of this material include: high dielectric constant (Dk), extremely low dissipation factor (Df), good ductility, and good thermal performance.

TYPICAL PROPERTY VALUES

Revision 20191216

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	55	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	46	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	8.7	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	14	%	ASTM D 638
Tensile Modulus, 50 mm/min	2530	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	85	MPa	ASTM D 790
Flexural Stress, brk, 1.3 mm/min, 50 mm span	83	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2350	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	49	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7.9	%	ISO 527
Tensile Strain, break, 50 mm/min	16	%	ISO 527
Tensile Modulus, 1 mm/min	2490	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Stress, break, 2 mm/min	93	MPa	ISO 178
Flexural Modulus, 2 mm/min	2620	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	280	J/m	ASTM D 256
Izod Impact, notched, -20°C	145	J/m	ASTM D 256
Izod Impact, notched 80*10*4 +23°C	30	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -20°C	13	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	173	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	154	°C	ASTM D 648
CTE, -40°C to 150°C, flow	6.1E-05	1/°C	ASTM E 831
CTE, -40°C to 150°C, xflow	8.7E-05	1/°C	ASTM E 831
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	173	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	155	°C	ISO 75/Af
Relative Temp Index, Elec (1)	65	°C	UL 746B
Relative Temp Index, Mech w/impact (1)	65	°C	UL 746B
Relative Temp Index, Mech w/o impact (1)	65	°C	UL 746B
PHYSICAL			
Density	1.35	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.6 – 0.8	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.6 – 0.8	%	ISO 294

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Flow Rate, 300°C/5.0 kgf	11	g/10 min	ASTM D 1238
Melt Flow Rate, 300°C/10 kgf	36	g/10 min	ASTM D 1238
Density	1.35	g/cm³	ISO 1183
Water Absorption, 23°C/24hrs	0.03	%	ISO 62-1
Melt Volume Rate, MVR at 300°C/5.0 kg	9	cm³/10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/10.0 kg	30	cm³/10 min	ISO 1133
ELECTRICAL			
Dielectric Constant, 1.1 GHz	3.56	-	SABIC method
Dielectric Constant, 1.9 GHz	3.57	-	SABIC method
Dielectric Constant, 5 GHz	3.57	-	SABIC method
Dielectric Constant, 10 GHz	3.58	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0009	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0011	-	SABIC method
Dissipation Factor, 5 GHz	0.0019	-	SABIC method
Dissipation Factor, 10 GHz	0.0022	-	SABIC method
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E207780-102719345	-	-
UL Recognized, 94HB Flame Class Rating	1	mm	UL 94
INJECTION MOLDING			
Drying Temperature	105	°C	
Drying Time	3 – 5	hrs	
Melt Temperature	295 – 305	°C	
Nozzle Temperature	290 – 295	°C	
Front - Zone 3 Temperature	300 – 305	°C	
Middle - Zone 2 Temperature	290 – 295	°C	
Rear - Zone 1 Temperature	280 – 285	°C	
Mold Temperature	90	°C	
Back Pressure	9	MPa	
Screw Speed	100	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved