LNP™ LUBRILOY™ COMPOUND RF206AXH

RF-30 HC

DESCRIPTION

LNP LUBRILOY* RF206AXH is a compound based on Nylon 66 resin containing 30% Glass Fiber, Proprietary Lubricant, Added features of this material include: Wear Resistant, Healthcare.

TYPICAL PROPERTY VALUES

Revision 20191211

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	121	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	8760	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	173	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	7060	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	118	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.3	%	ISO 527
Tensile Modulus, 1 mm/min	8460	MPa	ISO 527
Flexural Stress	167	MPa	ISO 178
Flexural Modulus, 2 mm/min	7200	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	690	J/m	ASTM D 4812
Izod Impact, notched, 23°C	114	J/m	ASTM D 256
Multiaxial Impact	3	J	ISO 6603
Instrumented Impact Total Energy, 23°C	13	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	35	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	9	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	258	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	241	°C	ASTM D 648
CTE, -30°C to 30°C, flow	3.8E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	7.5E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	252	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	224	°C	ISO 75/Af
PHYSICAL			
Density	1.24	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.38	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.6	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.2	%	ASTM D 955
Wear Factor Washer	45	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.4	-	ASTM D 3702 Modified: Manual
Static COF	0.4	-	ASTM D 3702 Modified: Manual
Moisture Absorption (23°C / 50% RH)	0.66	%	ISO 62
INJECTION MOLDING			

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	270 – 280	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved