LNP™ LUBRICOMP™ COMPOUND DFP36

DFL-4536
REGION EUROPE

DESCRIPTION

LNP* LUBRICOMP* DFP36 is a compound based on Polycarbonate resin containing 30% Glass Fiber, 15% PTFE/Silicone. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break, 5 mm/min	98	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	8700	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	127	MPa	ISO 178
Flexural Modulus, 2 mm/min	5200	MPa	ISO 178
IMPACT			
Izod Impact, notched 80*10*4 +23°C	13	kJ/m²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	2.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	5.1E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	145	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	140	°C	ISO 75/Af
Relative Temp Index, Elec (1)	80	°C	UL 746B
Relative Temp Index, Mech w/impact (1)	80	°C	UL 746B
Relative Temp Index, Mech w/o impact (1)	80	°C	UL 746B
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E45329-101344674	-	-
UL Recognized, 94V-1 Flame Class Rating	≥2.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved