LNP™ LUBRICOMP™ COMPOUND DI001E

DESCRIPTION

LNP LUBRICOMP DI001E is a compound based on Polycarbonate resin containing Silicone. Added features include: Internally Lubricated, Easy Molding.

TYPICAL PROPERTY VALUES

Revision 20191210

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield, 5 mm/min	57	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	5.5	%	ISO 527
Tensile Modulus, 1 mm/min	2200	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	2100	MPa	ISO 178
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	165	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	40	kJ/m²	ISO 180/1A
THERMAL			
CTE, 23°C to 60°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 60°C, xflow	7.2E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	137	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	124	°C	ISO 75/Af
PHYSICAL			
Density	1.19	g/cm³	ISO 1183
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 315	°C	
Front - Zone 3 Temperature	310 – 320	°C	
Middle - Zone 2 Temperature	305 – 315	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved