LNP™ LUBRICOMP™ COMPOUND OCL36

OCL-4036
REGION ASIA

DESCRIPTION

LNP LUBRICOMP* OCL36 is a compound based on PPS - Linear resin containing 30% Carbon Fiber, 15% PTFE. Added features of this material include: Electrically Conductive, Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20190412

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	168	MPa	ASTM D 638
Tensile Strain, break	1.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	21510	MPa	ASTM D 638
Flexural Stress	259	MPa	ASTM D 790
Flexural Modulus	21110	MPa	ASTM D 790
Tensile Stress, break	166	MPa	ISO 527
Tensile Strain, break	1.1	%	ISO 527
Tensile Modulus, 1 mm/min	30680	MPa	ISO 527
Flexural Stress	262	MPa	ISO 178
Flexural Modulus	21200	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	443	J/m	ASTM D 4812
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	15	J	ASTM D 3763
Multiaxial Impact	2	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	31	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	6	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	267	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	263	°C	ISO 75/Af
PHYSICAL			
Density	1.52	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	0.04 – 0.1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.3 – 0.4	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.04 – 0.1	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.36 – 0.4	%	ISO 294
Wear Factor Washer	19	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.39	-	ASTM D 3702 Modified: Manual
Static COF	0.34	-	ASTM D 3702 Modified: Manual
Density	1.52	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.03	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120 – 150	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	hrs	
Melt Temperature	315 – 320	°C	
Front - Zone 3 Temperature	330 – 345	°C	
Middle - Zone 2 Temperature	320 – 330	°C	
Rear - Zone 1 Temperature	305 – 315	°C	
Mold Temperature	140 – 165	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved