NORYL™ RESIN GFN2

REGION ASIA

DESCRIPTION

NORYL™ GFN2 resin is a 20% glass reinforced blend of polyphenylene ether (PPE) + high impact polystyrene (HIPS). This general-purpose injection moldable grade exhibits very low moisture absorption, high strength, hydrolytic stability, Low warpage, low specific gravity, and dimensional stability. NORYL GFN2 carries a UL746C outdoor suitability rating of F1 and is an excellent candidate for a variety of indoor and outdoor applications including construction, electrical components + displays, lawn and garden equipment. *See NORYL GFN2F resin for FDA food compliant / NSF version.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	100	MPa	ASTM D 638
Tensile Stress, yld, Type I, 10 mm/min	88	MPa	SABIC - Japan Method
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, yld, Type I, 10 mm/min	6 – 8	%	SABIC - Japan Method
Tensile Modulus, 5 mm/min	6500	MPa	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	131	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	5570	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	90	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3	%	ISO 527
Tensile Modulus, 1 mm/min	6000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	150	MPa	ISO 178
Flexural Modulus, 2 mm/min	5400	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	550	J/m	ASTM D 4812
Izod Impact, notched, 23°C	88	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	20	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	9	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	8	kJ/m²	ISO 179/1eA
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	137	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	138	°C	ASTM D 648
CTE, -30°C to 30°C	0.000028 – 0.000045	1/°C	TMA
Vicat Softening Temp, Rate B/50	140	°C	ISO 306
Vicat Softening Temp, Rate B/120	147	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	135	°C	ISO 75/Af
Relative Temp Index, Elec (1)	90	°C	UL 746B
Relative Temp Index, Mech w/impact (1)	90	°C	UL 746B
Relative Temp Index, Mech w/o impact (1)	90	°C	UL 746B
PHYSICAL			
Specific Gravity	1.23	-	ASTM D 792

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, 24 hours	0.06	%	ASTM D 570
Mold Shrinkage, flow	0.2 – 0.4	%	SABIC method
Melt Flow Rate, 300°C/5.0 kgf	11.7	g/10 min	ASTM D 1238
Water Absorption, 23°C/24hrs	0.12	%	ISO 62-1
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 280°C/5.0 kg	2	cm³/10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E207780-228545	-	-
UL Yellow Card Link 2	E45587-237020	-	-
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	110 – 120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	300 – 325	°C	
Nozzle Temperature	300 – 325	°C	
Front - Zone 3 Temperature	290 – 325	°C	
Middle - Zone 2 Temperature	275 – 320	°C	
Rear - Zone 1 Temperature	265 – 315	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	20 – 100	rpm	
Shot to Cylinder Size	30 – 70	%	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved