# LNP™ LUBRICOMP™ COMPOUND QFL32

QFL-4032

## DESCRIPTION

LNP LUBRICOMP QFL32 is a compound based on Nylon 6/10 containing 10% Glass Fiber, 15% PTFE. Added features of this grade include: Wear Resistant.

## TYPICAL PROPERTY VALUES

Revision 20191210

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| MECHANICAL | | | |
| Tensile Stress, brk, Type I, 5 mm/min | 85 | MPa | ASTM D 638 |
| Tensile Strain, brk, Type I, 5 mm/min | 3.1 | % | ASTM D 638 |
| Tensile Modulus, 50 mm/min | 4680 | MPa | ASTM D 638 |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 134 | MPa | ASTM D 790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 3850 | MPa | ASTM D 790 |
| Tensile Stress, yield, 5 mm/min | 86 | MPa | ISO 527 |
| Tensile Stress, break, 5 mm/min | 79 | MPa | ISO 527 |
| Tensile Strain, break, 5 mm/min | 3 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 4440 | MPa | ISO 527 |
| Flexural Stress | 128 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 3880 | MPa | ISO 178 |
| IMPACT | | | |
| Izod Impact, unnotched, 23°C | 367 | J/m | ASTM D 4812 |
| Izod Impact, notched, 23°C | 38 | J/m | ASTM D 256 |
| Multiaxial Impact | 1 | J | ISO 6603 |
| Instrumented Impact Total Energy, 23°C | 5 | J | ASTM D 3763 |
| Izod Impact, unnotched 80*10*4 +23°C | 23 | kJ/m² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 1 | kJ/m² | ISO 180/1A |
| THERMAL | | | |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 218 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 196 | °C | ASTM D 648 |
| CTE, -30°C to 30°C, flow | 5.64E+01 | 1/°C | ASTM D 696 |
| CTE, -30°C to 30°C, xflow | 1.18E+02 | 1/°C | ASTM D 696 |
| HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm | 215 | °C | ISO 75/Bf |
| HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm | 189 | °C | ISO 75/Af |
| PHYSICAL | | | |
| Specific Gravity | 1.25 | - | ASTM D 792 |
| Moisture Absorption, 50% RH, 24 hrs | 0.24 | % | ASTM D 570 |
| Mold Shrinkage, flow, 24 hrs | 0.7 – 0.9 | % | ASTM D 955 |
| Mold Shrinkage, xflow, 24 hrs | 1 – 3 | % | ASTM D 955 |
| Wear Factor Washer | 48 | 10^-10 in^5-min/ft-lb-hr | ASTM D 3702 Modified: Manual |
| Wear Factor Ring | 5 | 10^-10 in^5-min/ft-lb-hr | ASTM D 3702 Modified: Manual |
| Dynamic COF | 0.42 | - | ASTM D 3702 Modified: Manual |
| Static COF | 0.38 | - | ASTM D 3702 Modified: Manual |

© 2019 Copyright by SABIC. All rights reserved

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|---|---|---|
| Density | 1.25 | g/cm³ | ISO 1183 |
| Moisture Absorption (23°C / 50% RH) | 0.34 | % | ISO 62 |
| INJECTION MOLDING | | | |
| Drying Temperature | 80 | °C | |
| Drying Time | 4 | hrs | |
| Maximum Moisture Content | 0.12 – 0.2 | % | |
| Melt Temperature | 270 – 275 | °C | |
| Front - Zone 3 Temperature | 270 – 280 | °C | |
| Middle - Zone 2 Temperature | 260 – 270 | °C | |
| Rear - Zone 1 Temperature | 250 – 260 | °C | |
| Mold Temperature | 80 – 95 | °C | |
| Back Pressure | 0.2 – 0.3 | MPa | |
| Screw Speed | 30 – 60 | rpm | |

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved