LNP™ LUBRICOMP™ COMPOUND RAL23

RAL-4023
REGION ASIA

DESCRIPTION

LNP LUBRICOMP* RAL23 is a compound based on Nylon 66 resin containing 15% Aramid Fiber, 10% PTFE. Added features of this material include: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20190801

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	89	MPa	ASTM D 638
Tensile Strain, break	5.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	3680	MPa	ASTM D 638
Flexural Stress	131	MPa	ASTM D 790
Flexural Modulus	3930	MPa	ASTM D 790
Tensile Stress, break	85	MPa	ISO 527
Tensile Strain, break	6.3	%	ISO 527
Tensile Modulus, 1 mm/min	3800	MPa	ISO 527
Flexural Stress	107	MPa	ISO 178
Flexural Modulus	3500	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	534	J/m	ASTM D 4812
Izod Impact, notched, 23°C	46	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	37	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	171	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.66E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.72E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.8E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.8E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	246	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Af
PHYSICAL			
Density	1.24	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	1.7 – 1.8	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	2 – 2.1	%	ASTM D 955
Wear Factor Washer	23	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.38	-	ASTM D 3702 Modified: Manual
Static COF	0.32	-	ASTM D 3702 Modified: Manual
Density	1.23	g/cm³	ISO 1183
INJECTION MOLDING			
Drying Temperature	80	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	275 – 290	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	80 – 95	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved