LNP™ LUBRICOMP™ COMPOUND RP003

RL-4530
REGION ASIA

DESCRIPTION

LNP LUBRICOMP RP003 is a compound based on Nylon 66 resin containing 15% PTFE/Silicone. Added feature of this material is: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20191108

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	48	MPa	ASTM D 638
Tensile Strain, yield	4.6	%	ASTM D 638
Tensile Strain, break	4.7	%	ASTM D 638
Tensile Modulus, 50 mm/min	2700	MPa	ASTM D 638
Flexural Stress	68	MPa	ASTM D 790
Flexural Modulus	2060	MPa	ASTM D 790
Tensile Stress, yield	55	MPa	ISO 527
Tensile Stress, break	55	MPa	ISO 527
Tensile Strain, yield	4.7	%	ISO 527
Tensile Strain, break	4.7	%	ISO 527
Tensile Modulus, 1 mm/min	2960	MPa	ISO 527
Flexural Stress	85	MPa	ISO 178
Flexural Modulus	3000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	379	J/m	ASTM D 4812
Izod Impact, notched, 23°C	37	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	1	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	26	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	4	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	201	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	59	°C	ASTM D 648
CTE, -40°C to 40°C, flow	9.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	9.54E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	9.1E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	9.6E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	221	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	66	°C	ISO 75/Af
PHYSICAL			
Density	1.27	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.6	%	ASTM D 570
Wear Factor Washer	10	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.22	-	ASTM D 3702 Modified: Manual

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Static COF	0.16	-	ASTM D 3702 Modified: Manual
Density	1.27	g/cm³	ISO 1183

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved