LNP™ LUBRICOMP™ COMPOUND UFL36SXC

UFL-4036 HS
REGION ASIA

DESCRIPTION

LNP LUBRICOMP UFL36SXC is a compound based on Polyphthalamide resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant, Heat Stabilized.

TYPICAL PROPERTY VALUES

Revision 20191114

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, break	196	MPa	ASTM D 638
Tensile Strain, break	2.5	%	ASTM D 638
Tensile Modulus, 50 mm/min	12410	MPa	ASTM D 638
Flexural Stress	275	MPa	ASTM D 790
Flexural Modulus	10820	MPa	ASTM D 790
Tensile Stress, break	196	MPa	ISO 527
Tensile Strain, break	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	9880	MPa	ISO 527
Flexural Stress	286	MPa	ISO 178
Flexural Modulus	11230	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1014	J/m	ASTM D 4812
Izod Impact, notched, 23°C	117	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	7	J	ASTM D 3763
Multiaxial Impact	3	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	70	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	260	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	255	°C	ISO 75/Af
PHYSICAL			
Density	1.55	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.3	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.2	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.8	%	ASTM D 955
Mold Shrinkage, flow, 24 hrs	0.17	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.82	%	ISO 294
Wear Factor Washer	6	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.46	-	ASTM D 3702 Modified: Manual
Static COF	0.49	-	ASTM D 3702 Modified: Manual
Density	1.55	g/cm³	ISO 1183

© 2019 Copyright by SABIC. All rights reserved

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved