LNP™ LUBRICOMP™ COMPOUND WL002

WL-4020

DESCRIPTION

LNP LUBRICOMP WL002 is a compound based on PBT resin containing 10% PTFE. Added feature of this grade is: Wear Resistant.

TYPICAL PROPERTY VALUES

Revision 20191218

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	52	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	51	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	9.3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	12	%	ASTM D 638
Tensile Modulus, 50 mm/min	2780	MPa	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	2640	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	51	MPa	ISO 527
Tensile Stress, break, 5 mm/min	51	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	9.8	%	ISO 527
Tensile Strain, break, 5 mm/min	10.9	%	ISO 527
Tensile Modulus, 1 mm/min	2900	MPa	ISO 527
Flexural Stress	78	MPa	ISO 178
Flexural Modulus, 2 mm/min	2340	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	880	J/m	ASTM D 4812
Izod Impact, notched, 23°C	39	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	6	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	53	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	3	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	182	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	58	°C	ASTM D 648
CTE, -30°C to 30°C, flow	9.78E+01	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	9.88E+01	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	160	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	57	°C	ISO 75/Af
PHYSICAL			
Density	1.38	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	2 – 4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	2 – 4	%	ASTM D 955
Wear Factor Washer	25	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Wear Factor Ring	2	10^-10 in^5-min/ft-lb-hr	ASTM D 3702 Modified: Manual
Dynamic COF	0.35	-	ASTM D 3702 Modified: Manual
Static COF	0.31	-	ASTM D 3702 Modified: Manual

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.38	g/cm³	ISO 1183
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.05	%	
Melt Temperature	240 – 265	°C	
Front - Zone 3 Temperature	260 – 270	°C	
Middle - Zone 2 Temperature	245 – 255	°C	
Rear - Zone 1 Temperature	220 – 230	°C	
Mold Temperature	80 – 100	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved