

LEXANTM COPOLYMER 4504

REGION ASIA

DESCRIPTION

High heat resistant polycarbonate copolymer, provides DTUL of 290F at 264 psi. FDA food contact compliant in limited colors. Effective January 15th, 2008 this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HPH4504.

TYPICAL PROPERTY VALUES

Revision 20191031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	71	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	122	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2020	MPa	ASTM D 790
Hardness, Rockwell M	85	-	ASTM D 785
Hardness, Rockwell R	122	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D 4812
Izod Impact, notched, 23°C	640	J/m	ASTM D 256
Tensile Impact Strength, Type S	577	kJ/m ²	ASTM D 1822
Falling Dart Impact (D 3029), 23°C	149	J	ASTM D 3029
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	143	°C	ASTM D 648
CTE, -40°C to 95°C, flow	9.18E-05	1/°C	ASTM E 831
Specific Heat	1.26	J/g·°C	ASTM C 351
Thermal Conductivity	0.21	W/m·°C	ASTM C 177
Relative Temp Index, Elec	125	°C	UL 746B
Relative Temp Index, Mech w/impact	125	°C	UL 746B
Relative Temp Index, Mech w/o impact	125	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D 792
Specific Volume	0.83	cm ³ /g	ASTM D 792
Density	1.19	g/cm ³	ASTM D 792
Water Absorption, 24 hours	0.16	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.7 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	3	g/10 min	ASTM D 1238
OPTICAL			
Light Transmission, 2.54 mm	85	%	ASTM D 1003
Haze, 2.54 mm	1	%	ASTM D 1003
Refractive Index	1.6	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>2.6E+17	Ohm-cm	ASTM D 257

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dielectric Strength, in air, 3.2 mm	20.3	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	3.15	-	ASTM D 150
Relative Permittivity, 1 MHz	3	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0012	-	ASTM D 150
Dissipation Factor, 100 Hz	0.024	-	ASTM D 150
Hot Wire Ignition {PLC}	2	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	3	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	340 – 360	°C	
Nozzle Temperature	330 – 355	°C	
Front - Zone 3 Temperature	340 – 360	°C	
Middle - Zone 2 Temperature	325 – 350	°C	
Rear - Zone 1 Temperature	315 – 340	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.