

LEXAN™ COPOLYMER CXT19

REGION ASIA

DESCRIPTION

LEXAN™ CXT19 Resin is a High Heat Polycarbonate Copolymer Resin with Vicat of 190°C and crystal clear transparency. This resin is optimized to have a broad processing window with limited yellowing. It is available in limited transparent colors.

TYPICAL PROPERTY VALUES

Revision 20190103

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	80	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	7.5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	>25	%	ASTM D 638
Tensile Modulus, 5 mm/min	2600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	120	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2600	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	80	MPa	ISO 527
Tensile Stress, break, 50 mm/min	65	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	7	%	ISO 527
Tensile Strain, break, 50 mm/min	>25	%	ISO 527
Tensile Modulus, 1 mm/min	2500	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	120	MPa	ISO 178
Flexural Modulus, 2 mm/min	2550	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	80	J/m	ASTM D 256
Izod Impact, notched, -30°C	70	J/m	ASTM D 256
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	8	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	9	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	7	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Tg (half width)	195	°C	SABIC method
Vicat Softening Temp, Rate B/120	190	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	185	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	170	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.00E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.00E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/120	190	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	185	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	170	°C	ISO 75/Af
Thermal Conductivity	0.2	W/m·°C	ISO 8302

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Mold Shrinkage, flow, 3.2 mm	0.7 – 1.0	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.7 – 1.0	%	SABIC method
Specific Gravity	1.22	-	ASTM D 792
Melt Flow Rate, 330°C/2.16 kgf	17	g/10 min	ASTM D 1238
Melt Flow Rate, 350°C/2.16 kgf	33	g/10 min	ASTM D 1238
Density	1.22	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.5	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.3	%	ISO 62
Melt Volume Rate, MVR at 330°C/2.16kg	15	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 350°C/2.16kg	30	cm ³ /10 min	ISO 1133
OPTICAL			
Refractive Index	1.609	-	ISO 489
Abbe number	30	-	ISO 489
Light Transmission, 1.0 mm	89	%	ASTM D1003
Light Transmission at 2.0 mm	88	%	ASTM D1003
Light Transmission at 3.0 mm	87	%	ASTM D1003
INJECTION MOLDING			
Drying Temperature	135	°C	
Drying Time	5 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 350	°C	
Nozzle Temperature	305 – 345	°C	
Front - Zone 3 Temperature	310 – 350	°C	
Middle - Zone 2 Temperature	300 – 340	°C	
Rear - Zone 1 Temperature	280 – 330	°C	
Mold Temperature	120 – 170	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.