

LEXANTM COPOLYMER EXL1434

REGION ASIA

DESCRIPTION

LEXAN EXL1434 polycarbonate (PC) siloxane copolymer resin is a medium flow opaque injection molding (IM) grade and is UV stabilized. This resin offers extreme low temperature (-40 C), exhibits excellent processability and release with opportunities for shorter IM cycle times compared to standard PC. LEXAN EXL1434 resin is a product available in wide range of opaque colors and may be an excellent candidate for a wide variety of applications.

TYPICAL PROPERTY VALUES

Revision 20190510

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------|--------------|
| MECHANICAL | | | |
| Tensile Stress, yld, Type I, 50 mm/min | 55 | MPa | ASTM D 638 |
| Tensile Stress, brk, Type I, 50 mm/min | 50 | MPa | ASTM D 638 |
| Tensile Strain, yld, Type I, 50 mm/min | 6 | % | ASTM D 638 |
| Tensile Strain, brk, Type I, 50 mm/min | 98 | % | ASTM D 638 |
| Tensile Modulus, 50 mm/min | 2020 | MPa | ASTM D 638 |
| Flexural Stress, yld, 1.3 mm/min, 50 mm span | 92 | MPa | ASTM D 790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 2230 | MPa | ASTM D 790 |
| Hardness, Rockwell L | 89 | - | ASTM D 785 |
| Hardness, Rockwell R | 121 | - | ASTM D 785 |
| Tensile Stress, yield, 50 mm/min | 57 | MPa | ISO 527 |
| Tensile Stress, break, 50 mm/min | 60 | MPa | ISO 527 |
| Tensile Strain, yield, 50 mm/min | 6 | % | ISO 527 |
| Tensile Strain, break, 50 mm/min | 120 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 2150 | MPa | ISO 527 |
| Flexural Stress, yield, 2 mm/min | 85 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 2250 | MPa | ISO 178 |
| IMPACT | | | |
| Izod Impact, notched, 23°C | 865 | J/m | ASTM D 256 |
| Izod Impact, notched, -30°C | 774 | J/m | ASTM D 256 |
| Instrumented Impact Total Energy, 23°C | 70 | J | ASTM D 3763 |
| Izod Impact, unnotched 80*10*3 +23°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*3 -30°C | NB | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*3 +23°C | 70 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*3 -30°C | 60 | kJ/m ² | ISO 180/1A |
| Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm | 70 | kJ/m ² | ISO 179/1eA |
| Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm | 65 | kJ/m ² | ISO 179/1eA |
| Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm | NB | kJ/m ² | ISO 179/1eU |
| THERMAL | | | |
| Vicat Softening Temp, Rate B/50 | 145 | °C | ASTM D 1525 |
| HDT, 0.45 MPa, 3.2 mm, unannealed | 139 | °C | ASTM D 648 |
| HDT, 1.82 MPa, 3.2mm, unannealed | 124 | °C | ASTM D 648 |
| CTE, -40°C to 40°C, flow | 7.0E-05 | 1/°C | ASTM E 831 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|---|-----------------------------------|-------------------------|----------------|
| CTE, -40°C to 40°C, xflow | 7.47E-05 | 1/°C | ASTM E 831 |
| CTE, 23°C to 80°C, flow | 7.2E-05 | 1/°C | ISO 11359-2 |
| CTE, 23°C to 80°C, xflow | 7.2E-05 | 1/°C | ISO 11359-2 |
| Ball Pressure Test, 125°C +/- 2°C | Passes | - | IEC 60695-10-2 |
| Vicat Softening Temp, Rate B/50 | 145 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 146 | °C | ISO 306 |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm | 140 | °C | ISO 75/Be |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 128 | °C | ISO 75/Ae |
| Relative Temp Index, Elec ⁽¹⁾ | 130 | °C | UL 746B |
| Relative Temp Index, Mech w/impact ⁽¹⁾ | 120 | °C | UL 746B |
| Relative Temp Index, Mech w/o impact ⁽¹⁾ | 130 | °C | UL 746B |
| PHYSICAL | | | |
| Specific Gravity | 1.18 | - | ASTM D 792 |
| Mold Shrinkage, flow, 3.2 mm | 0.4 – 0.8 | % | SABIC method |
| Mold Shrinkage, xflow, 3.2 mm | 0.4 – 0.8 | % | SABIC method |
| Melt Flow Rate, 300°C/1.2 kgf | 10 | g/10 min | ASTM D 1238 |
| Density | 1.19 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/sat) | 0.35 | % | ISO 62 |
| Moisture Absorption (23°C / 50% RH) | 0.15 | % | ISO 62 |
| Melt Volume Rate, MVR at 300°C/1.2 kg | 9 | cm ³ /10 min | ISO 1133 |
| ELECTRICAL | | | |
| Volume Resistivity | >1.E+15 | Ohm-cm | ASTM D 257 |
| Surface Resistivity | >1.E+15 | Ohm | ASTM D 257 |
| Dielectric Strength, in oil, 0.8 mm | 16.2 | kV/mm | ASTM D 149 |
| Relative Permittivity, 100 Hz | 2.68 | - | ASTM D 150 |
| Relative Permittivity, 1 MHz | 2.64 | - | ASTM D 150 |
| Dissipation Factor, 100 Hz | 0.0012 | - | ASTM D 150 |
| Dissipation Factor, 1 MHz | 0.0093 | - | ASTM D 150 |
| Hot-Wire Ignition (HWI), PLC 0 | ≥0.7 | mm | UL 746A |
| High Amp Arc Ignition (HAI), PLC 1 | ≥0.7 | mm | UL 746A |
| FLAME CHARACTERISTICS ⁽¹⁾ | | | |
| UL Yellow Card Link | E207780-100079880 | - | - |
| UL Yellow Card Link 2 | E207780-475370 | - | - |
| UL Recognized, 94HB Flame Class Rating | ≥0.7 | mm | UL 94 |
| Glow Wire Ignitability Temperature, 3.0 mm | 875 | °C | IEC 60695-2-13 |
| Glow Wire Ignitability Temperature, 1.0 mm | 875 | °C | IEC 60695-2-13 |
| Glow Wire Ignitability Temperature, 1.5 mm | 875 | °C | IEC 60695-2-13 |
| Glow Wire Ignitability Temperature, 0.8 mm | 875 | °C | IEC 60695-2-13 |
| Glow Wire Flammability Index, 3.0 mm | 960 | °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 1.5 mm | 960 | °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 1.0 mm | 960 | °C | IEC 60695-2-12 |
| Glow Wire Flammability Index, 0.8 mm | 850 | °C | IEC 60695-2-12 |
| UV-light, water exposure/immersion | F1 | - | UL 746C |
| Oxygen Index (LOI) | 37 | % | ISO 4589 |
| INJECTION MOLDING | | | |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|-----------------------------|----------------|-------|--------------|
| Drying Temperature | 120 | °C | |
| Drying Time | 3 – 4 | hrs | |
| Drying Time (Cumulative) | 48 | hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 295 – 315 | °C | |
| Nozzle Temperature | 290 – 310 | °C | |
| Front - Zone 3 Temperature | 295 – 315 | °C | |
| Middle - Zone 2 Temperature | 280 – 305 | °C | |
| Rear - Zone 1 Temperature | 270 – 295 | °C | |
| Mold Temperature | 70 – 95 | °C | |
| Back Pressure | 0.3 – 0.7 | MPa | |
| Screw Speed | 40 – 70 | rpm | |
| Shot to Cylinder Size | 40 – 60 | % | |
| Vent Depth | 0.025 – 0.076 | mm | |

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.