

LEXANTM COPOLYMER EXL1494T

REGION ASIA

DESCRIPTION

LEXAN EXL1494T polycarbonate (PC) siloxane copolymer resin is an injection molding grade with FDA and EU food contact compliance. This resin offers extreme low temperature (-40 C) ductility in combination with medium flow characteristics, improved release and excellent processability with opportunities for shorter IM cycle times compared to standard PC. LEXAN EXL1494T resin is available in transparent and opaque colors and is an excellent candidate for a broad range of food contact applications.

TYPICAL PROPERTY VALUES

Revision 20191031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	59	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	123.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	2180	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	92	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2180	MPa	ASTM D 790
Hardness, Rockwell L	87	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	56	MPa	ISO 527
Tensile Stress, break, 50 mm/min	55	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.4	%	ISO 527
Tensile Strain, break, 50 mm/min	108.5	%	ISO 527
Tensile Modulus, 1 mm/min	2300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	88	MPa	ISO 178
Flexural Modulus, 2 mm/min	2120	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	824	J/m	ASTM D 256
Izod Impact, notched, -30°C	712	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	75	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	77	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	65	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	55	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	70	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	138	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
CTE, -40°C to 95°C, flow	6.7E-05	1/°C	ASTM E 831

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 95°C, xflow	8.E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	6.7E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	8.E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	139	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	116	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	120	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	82	%	ASTM D 1003
Haze, 2.54 mm	3	%	ASTM D 1003
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+15	Ohm	ASTM D 257
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-466358	-	-
UL Recognized, 94V-2 Flame Class Rating	≥3	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.5 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	850	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.8 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.5 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.8 mm	825	°C	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.