

LEXANTM COPOLYMER EXL4419

REGION ASIA

DESCRIPTION

LEXAN EXL4419 polycarbonate (PC) siloxane copolymer resin is a 9% Glass Fiber (GF) reinforced opaque injection molding (IM) grade. This medium flow resin offers much higher ductility, improved release characteristics and excellent processability with opportunities for shorter IM cycle times when compared to GF reinforced standard PC resins. LEXAN EXL4419 resin is available in opaque colors only and is an excellent candidate for a broad range of applications that require a combination of stiffness and ductility.

TYPICAL PROPERTY VALUES

Revision 20190606

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	53	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	44	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4.5	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	20	%	ASTM D 638
Tensile Modulus, 5 mm/min	3300	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	3200	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	55	MPa	ISO 527
Tensile Stress, break, 5 mm/min	43	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	4.5	%	ISO 527
Tensile Strain, break, 5 mm/min	12.5	%	ISO 527
Tensile Modulus, 1 mm/min	3300	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	3300	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	280	J/m	ASTM D 256
Izod Impact, notched, -30°C	110	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	40	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	25	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	10	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	25	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	15	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	145	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	135	°C	ASTM D 648
CTE, -40°C to 40°C, flow	4.07E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.94E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	4.07E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, -40°C to 40°C, xflow	6.94E-05	1/°C	ISO 11359-2
Ball Pressure Test, 75°C +/- 2°C	PASS	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	144	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	134	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.25	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.6	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	11	g/10 min	ASTM D 1238
Density	1.25	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.46	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm ³ /10 min	ISO 1133
ELECTRICAL			
Volume Resistivity	1.78E+17	Ohm-cm	ASTM D 257
Surface Resistivity	2.86E+17	Ohm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	31.5	kV/mm	ASTM D 149
Relative Permittivity, 1 MHz	3.04	-	ASTM D 150
Dissipation Factor, 1 MHz	0.0086	-	ASTM D 150
Dielectric Constant, 1.9 GHz	2.95	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0057	-	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-502956	-	-
UL Recognized, 94HB Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.