

LEXANTM COPOLYMER EXL9330

REGION ASIA

DESCRIPTION

Opaque PC-Siloxane copolymer with excellent processability. Non-chlorinated, non-brominated flame retardant product in most colors. UV-stabilized. UL rated f1 /V-0/5VA.

TYPICAL PROPERTY VALUES

Revision 20190718

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	61	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	130	%	ASTM D 638
Tensile Modulus, 50 mm/min	2100	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2060	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	55	MPa	ISO 527
Tensile Stress, break, 50 mm/min	60	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	125	%	ISO 527
Tensile Modulus, 1 mm/min	2100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	85	MPa	ISO 178
Flexural Modulus, 2 mm/min	2200	MPa	ISO 178
Ball Indentation Hardness, H358/30	90	MPa	ISO 2039-1
IMPACT			
Izod Impact, notched, 23°C	801	J/m	ASTM D 256
Izod Impact, notched, -30°C	678	J/m	ASTM D 256
Izod Impact, notched, -50°C	587	J/m	ASTM D 256
Izod Impact, notched, 23°C, 6.4mm	640	J/m	ASTM D 256
Izod Impact, double-gated, 23°C	1068	J/m	SABIC method
Instrumented Impact Total Energy, 23°C	52	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	70	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	55	kJ/m ²	ISO 180/1A
Izod Impact, notched 63.5*12.7*3.2, 23°C	80	kJ/m ²	ISO 180/4A
Izod Impact, notched 63.5*12.7*3.2, -30°C	65	kJ/m ²	ISO 180/4A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	75	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	60	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	142	°C	ASTM D 1525

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	134	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	120	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	124	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.66E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.66E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	7.2E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.7E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	140	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	135	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	124	°C	ISO 75/Ae
Relative Temp Index, Elec ⁽¹⁾	125	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	115	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	125	°C	UL 746B
PHYSICAL			
Specific Gravity	1.18	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.35	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.15	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Strength, in oil, 3.2 mm	17	kV/mm	ASTM D 149
Relative Permittivity, 50/60 Hz	2.95	-	ASTM D 150
Relative Permittivity, 1 MHz	2.9	-	ASTM D 150
Dissipation Factor, 50/60 Hz	0.0024	-	ASTM D 150
Dissipation Factor, 1 MHz	0.0085	-	ASTM D 150
Volume Resistivity	>1.E+15	Ohm-cm	IEC 60093
Surface Resistivity, ROA	>1.E+15	Ohm	IEC 60093
Dielectric Strength, in oil, 3.2 mm	16	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.7	-	IEC 60250
Dissipation Factor, 50/60 Hz	0.001	-	IEC 60250
Dissipation Factor, 1 MHz	0.0085	-	IEC 60250
Comparative Tracking Index	225	V	IEC 60112
Relative Permittivity, 50/60 Hz	2.6	-	IEC 60250
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥0.6	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 0	≥2.3	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 1	≥0.6	mm	UL 746A
FLAME CHARACTERISTICS ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Yellow Card Link	<u>E207780-102516601</u>	-	-
UL Yellow Card Link 2	<u>E207780-228378</u>	-	-
UL Recognized, 94-5VA Flame Class Rating	≥3	mm	UL 94
UL Recognized, 94-5VB Flame Class Rating	≥2.5	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥1.5	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating	≥0.8	mm	UL 94
UL Recognized, 94HB Flame Class Rating	≥0.6	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.5 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.3 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.5 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.3 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	960	°C	IEC 60695-2-12
Oxygen Index (LOI)	35	%	ISO 4589
UV-light, water exposure /immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	265 – 315	°C	
Nozzle Temperature	260 – 310	°C	
Front - Zone 3 Temperature	265 – 315	°C	
Middle - Zone 2 Temperature	255 – 305	°C	
Rear - Zone 1 Temperature	245 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.