

# LEXAN™ COPOLYMER FST3403

REGION ASIA

## DESCRIPTION

LEXAN FST3403 resin is a high flow PC Copolymer Resin, suitable for injection molding. This halogen-free flame retardant resin is EN45545 R6 HL3 compliant and an ideal candidate for train interior applications (category R6). It also meets requirements of DIN5510-2, NFPA-130 and PN-K-02511 standards. Available in opaque colors.

## TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	77	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	70	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	80	%	ASTM D 638
Tensile Modulus, 5 mm/min	2600	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	115	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2500	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	77	MPa	ISO 527
Tensile Stress, break, 50 mm/min	70	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	6	%	ISO 527
Tensile Strain, break, 50 mm/min	80	%	ISO 527
Tensile Modulus, 1 mm/min	2600	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	110	MPa	ISO 178
Flexural Modulus, 2 mm/min	2700	MPa	ISO 178
<b>IMPACT</b>			
Izod Impact, notched, 23°C	130	J/m	ASTM D 256
Izod Impact, notched, -30°C	90	J/m	ASTM D 256
Multiaxial Impact	125	J	ISO 6603
Instrumented Impact Total Energy, 23°C	80	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	13	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m <sup>2</sup>	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m <sup>2</sup>	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	13	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	5	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m <sup>2</sup>	ISO 179/1eA

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m <sup>2</sup>	ISO 179/1eU
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	114	°C	ASTM D 1525
HDT, 0.45 MPa, 3.2 mm, unannealed	104	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	93	°C	ASTM D 648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	114	°C	ISO 306
Vicat Softening Temp, Rate B/120	115	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Af
<b>PHYSICAL</b>			
Specific Gravity	1.33	-	ASTM D 792
Mold Shrinkage, flow	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	12	g/10 min	ASTM D 1238
Density	1.33	g/cm <sup>3</sup>	ISO 1183
Melt Volume Rate, MVR at 300°C/1.2 kg	10	cm <sup>3</sup> /10 min	ISO 1133
<b>FLAME CHARACTERISTICS</b>			
Heat release, MAHRE, 50 kW/m <sup>2</sup> , 3 mm	<60	kW/m <sup>2</sup>	ISO 5660-1
Smoke density, DS-4, 50 kW/m <sup>2</sup> , 3mm	<150	-	ISO 5659-2
Smoke density, VOF4, 50 kW/m <sup>2</sup> , 3mm	<300	-	ISO 5659-2
Smoke toxicity, CITG (8 min), 50 kW/m <sup>2</sup> , 3 mm	0.1	-	ISO 5659-2
Fire Safety Hazard Level - Requirement set R6	HL3	-	EN 45545-2:2013
<b>INJECTION MOLDING</b>			
Drying Temperature	95 – 100	°C	
Drying Time	6 – 8	hrs	
Melt Temperature	250 – 290	°C	
Nozzle Temperature	245 – 285	°C	
Front - Zone 3 Temperature	250 – 290	°C	
Middle - Zone 2 Temperature	240 – 280	°C	
Rear - Zone 1 Temperature	230 – 260	°C	
Mold Temperature	50 – 80	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.