

LEXANTM COPOLYMER FXE1414L

REGION ASIA

DESCRIPTION

Opaque EXL, UV-Stabilized & light shielding capability (Wall thickness >0.8mm), for portable electronics device enclosure application. Only available in white, grey and limited pastel colors. Consult CIC or PM for color availability & limitation.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	52	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	54	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	84	%	ASTM D 638
Tensile Modulus, 50 mm/min	2030	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	86	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2050	MPa	ASTM D 790
Tensile Stress, yield, 50 mm/min	52	MPa	ISO 527
Tensile Stress, break, 50 mm/min	47	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5	%	ISO 527
Tensile Strain, break, 50 mm/min	75	%	ISO 527
Tensile Modulus, 1 mm/min	2000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	83	MPa	ISO 178
Flexural Modulus, 2 mm/min	2110	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	766	J/m	ASTM D 256
Izod Impact, notched, -30°C	640	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	68	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	56	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	46	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	55	kJ/m ²	ISO 179/1eA
THERMAL			
Vicat Softening Temp, Rate B/50	138	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	121	°C	ASTM D 648
CTE, -40°C to 40°C, flow	7.E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.73E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	7.02E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.23E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	138	°C	ISO 306
Vicat Softening Temp, Rate B/120	146	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	118	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	80	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
PHYSICAL			
Specific Gravity	1.28	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/ 1.2 kgf	11	g/ 10 min	ASTM D 1238
Density	1.28	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.17	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.07	%	ISO 62
Melt Volume Rate, MVR at 300°C/ 1.2 kg	10	cm ³ / 10 min	ISO 1133
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-642296	-	-
UL Recognized, 94HB Flame Class Rating	0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	70 – 95	°C	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.