

LEXANTM COPOLYMER FXE4472L

REGION ASIA

DESCRIPTION

LEXAN FXE4472L is a 20% glass filled, impact modified polycarbonate with excellent light-shield capability. It is designed for high flow, superior surface appearance, enhance release and good impact ductility. FXE4472L is available in white color only and ideal for light-shield applications.

TYPICAL PROPERTY VALUES

Revision 20190514

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	38	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	44	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	6050	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	82	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	5200	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	920	J/m	ASTM D 4812
Izod Impact, notched, 23°C	170	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	23	J	ASTM D 3763
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	129	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	123	°C	ASTM D 648
Vicat Softening Temp, Rate B/120	134	°C	ISO 306
Relative Temp Index, Elec ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	80	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.33	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.3	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.5	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.33	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission at 0.4 mm	< 2	%	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-101621690	-	-
UL Recognized, 94HB Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	290 – 310	°C	
Nozzle Temperature	280 – 305	°C	
Front - Zone 3 Temperature	290 – 310	°C	
Middle - Zone 2 Temperature	275 – 300	°C	
Rear - Zone 1 Temperature	265 – 290	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.