

# LEXAN<sup>TM</sup> COPOLYMER FXEMPX2

REGION ASIA

## DESCRIPTION

LEXAN FXEMPX2 polycarbonate (PC) siloxane copolymer resin is a injection molding (IM) grade with release properties. This resin offers good low temperature ductility in combination with medium flow characteristics and excellent processability with opportunities for shorter IM cycle times compared to standard IM PC resins. LEXAN FXEMPX2 resin is a general purpose product available for wide range of colors and may be an excellent candidate for a broad range of applications.

## TYPICAL PROPERTY VALUES

Revision 20190607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	56	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	4.8	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	90	%	ASTM D 638
Tensile Modulus, 50 mm/min	2100	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	86	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D 790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	810	J/m	ASTM D 256
Izod Impact, notched, -30°C	650	J/m	ASTM D 256
<b>THERMAL</b>			
HDT, 1.82 MPa, 3.2mm, unannealed	116	°C	ASTM D 648
Ball Pressure Test, 125°C +/- 2°C	pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/120	138	°C	ISO 306
Relative Temp Index, Elec <sup>(1)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	80	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.18	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	14	g/10 min	ASTM D 1238
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	13	cm <sup>3</sup> /10 min	ISO 1133
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			
UL Yellow Card Link	<a href="#">E207780-102217430</a>	-	-
UL Recognized, 94HB Flame Class Rating	0.5	mm	UL 94
<b>INJECTION MOLDING</b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.