

LEXANTM COPOLYMER HPX4

REGION ASIA

DESCRIPTION

Medium flow specialty polycarbonate - improved processability & autoclavability. For medical devices and pharmaceutical applications. Healthcare management of change, biocompatible (ISO10993 or USP Class VI), EtO and steam sterilizable.

TYPICAL PROPERTY VALUES

Revision 20191031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	58	MPa	ASTM D 638
Tensile Stress, brk, Type I, 50 mm/min	64	MPa	ASTM D 638
Tensile Strain, yld, Type I, 50 mm/min	5.8	%	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	131.4	%	ASTM D 638
Tensile Modulus, 50 mm/min	2210	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	94	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2210	MPa	ASTM D 790
Hardness, Rockwell L	89	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	57	MPa	ISO 527
Tensile Stress, break, 50 mm/min	61	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	5.5	%	ISO 527
Tensile Strain, break, 50 mm/min	124.9	%	ISO 527
Tensile Modulus, 1 mm/min	2350	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	90	MPa	ISO 178
Flexural Modulus, 2 mm/min	2150	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	890	J/m	ASTM D 256
Izod Impact, notched, -30°C	795	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	82	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	85	J	ASTM D 3763
Izod Impact, unnotched 80*10*3 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*3 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*3 +23°C	65	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*3 -30°C	55	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*3 sp=62mm	65	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*3 sp=62mm	55	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*3 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate A/50	141	°C	ASTM D 1525
HDT, 1.82 MPa, 3.2mm, unannealed	124	°C	ASTM D 648
CTE, -40°C to 95°C, flow	7.15E-05	1/°C	ASTM E 831
CTE, -40°C to 95°C, xflow	7.93E-05	1/°C	ASTM E 831
CTE, 23°C to 80°C, flow	7.15E-05	1/°C	ISO 11359-2

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
CTE, 23°C to 80°C, xflow	7.93E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	pass	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	141	°C	ISO 306
Vicat Softening Temp, Rate B/120	142	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	118	°C	ISO 75/Af
Relative Temp Index, Elec ⁽¹⁾	130	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	120	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.19	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D 1238
Density	1.19	g/cm ³	ISO 1183
Water Absorption, (23°C/sat)	0.12	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.09	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	9	cm ³ /10 min	ISO 1133
OPTICAL			
Light Transmission, 2.54 mm	82	%	ASTM D 1003
Haze, 2.54 mm	3	%	ASTM D 1003
ELECTRICAL			
Volume Resistivity	>1.E+15	Ohm-cm	ASTM D 257
Surface Resistivity	>1.E+15	Ohm	ASTM D 257
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-100566198	-	-
UL Recognized, 94V-2 Flame Class Rating	≥2.5	mm	UL 94
UL Recognized, 94HB Flame Class Rating	≥1.5	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 2.5 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.8 mm	825	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2.5 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	825	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.8 mm	825	°C	IEC 60695-2-12
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	48	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Temperature	70 – 95	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.