LNP™ STAT-KON™ COMPOUND DX03550

PDX-D-03550
REGION ASIA

DESCRIPTION

LNP STAT-KON* DX03550 is a compound based on Polycarbonate resin containing Proprietary Filler(s). Added features of this material include: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20181031

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	58	MPa	ASTM D 638
Tensile Strain, break	20	%	ASTM D 638
Tensile Modulus, 50 mm/min	2750	MPa	ASTM D 638
Flexural Stress	96	MPa	ASTM D 790
Flexural Modulus	2750	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	NB	J/m	ASTM D 4812
Izod Impact, notched, 23°C	106	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	129	°C	ASTM D 648
PHYSICAL			
Density	1.25	g/cm³	ASTM D 792
ELECTRICAL			
Volume Resistivity	10000 – 10000000	Ohm-cm	ASTM D 257
Surface Resistivity	1.E+04 – 1.E+07	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	305 – 325	°C	
Front - Zone 3 Temperature	320 – 330	°C	
Middle - Zone 2 Temperature	310 – 320	°C	
Rear - Zone 1 Temperature	295 – 305	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2018 Copyright by SABIC. All rights reserved