LNP™ STAT-KON™ COMPOUND DX09315C

DESCRIPTION

LNP STAT-KON DX09315C is carbon fiber filled polycarbonate composite with good flow ability, and high level of cleanliness for the most demanding application. A unique feature of this material is its low C18-C40 hydrocarbons. This compound is manufactured using LNP CCS Technology.

TYPICAL PROPERTY VALUES

Revision 20191216

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	123	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Modulus, 5 mm/min	9810	MPa	ASTM D 638
Flexural Stress	201	MPa	ASTM D 790
Flexural Modulus	8130	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	732	J/m	ASTM D 4812
Izod Impact, notched, 23°C	94	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	125	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.3E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	7.E-05	1/°C	ASTM E 831
Relative Temp Index, Elec [1]	80	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	80	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	80	°C	UL 746B
PHYSICAL			
Specific Gravity	1.25	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.1 – 0.2	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.3 – 0.4	%	SABIC method
Melt Volume Rate, MVR at 300°C/2.16 kg	26	cm³/10 min	ISO 1133
ELECTRICAL			
Surface Resistivity	1.E+04 – 5.E+05	Ohm	ASTM D 257
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E207780-101901972	-	-
UL Recognized, 94HB Flame Class Rating	≥1	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 110	°C	
Drying Time	3 – 5	hrs	
Melt Temperature	280 – 320	°C	
Nozzle Temperature	280 – 320	°C	
Front - Zone 3 Temperature	280 – 320	°C	
Middle - Zone 2 Temperature	280 – 320	°C	
Rear - Zone 1 Temperature	250 – 280	°C	
Mold Temperature	90 – 120	°C	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Back Pressure	1 – 5	MPa	
Screw Speed	30 – 100	rpm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved