LNP™ STAT-KON™ COMPOUND FX91304

PDX-F-91304

DESCRIPTION

LNP STAT-KON FX91304 is a compound based on Polyethylene resin containing Proprietary Filler(s). Added feature of this grade is: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20191218

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	27	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	24	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	3	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3.6	%	ASTM D 638
Tensile Modulus, 50 mm/min	3000	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	35	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	1800	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	26	MPa	ISO 527
Tensile Stress, break, 5 mm/min	22	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2.8	%	ISO 527
Tensile Strain, break, 5 mm/min	3.7	%	ISO 527
Tensile Modulus, 1 mm/min	2420	MPa	ISO 527
Flexural Stress	36	MPa	ISO 178
Flexural Modulus, 2 mm/min	2110	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	505	J/m	ASTM D 4812
Izod Impact, notched, 23°C	166	J/m	ASTM D 256
Multiaxial Impact	4	J	ISO 6603
Instrumented Impact Total Energy, 23°C	10	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	31	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	97	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	72	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.9E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	2.32E-04	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	95	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	67	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	0.95	-	ASTM D 792
Density	0.94	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.01	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.4 – 0.7	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.2 – 0.5	%	ASTM D 955

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.02	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+06	Ohm	ASTM D 257
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	2 – 4	hrs	
Melt Temperature	230	°C	
Front - Zone 3 Temperature	220 – 230	°C	
Middle - Zone 2 Temperature	210 – 220	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	40 – 55	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved