LNP™ STAT-KON™ COMPOUND LX00486C

PDX-L-00486 CCS

DESCRIPTION

LNP* STAT-KON* LX00486C is a compound based on Polyetheretherketone containing proprietary fillers. Added features of this grade includes: Clean Compound System, Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20191212

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	179	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2	%	ASTM D 638
Tensile Modulus, 5 mm/min	17280	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	262	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	13600	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	177	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.2	%	ISO 527
Tensile Modulus, 1 mm/min	16280	MPa	ISO 527
Flexural Stress	255	MPa	ISO 178
Flexural Modulus, 2 mm/min	13490	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	657	J/m	ASTM D 4812
Izod Impact, notched, 23°C	63	J/m	ASTM D 256
Multiaxial Impact	2	J	ISO 6603
Instrumented Impact Total Energy, 23°C	6	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	40	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	336	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	315	°C	ASTM D 648
CTE, -30°C to 30°C, flow	1.1E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	4.1E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	330	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	291	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.4	-	ASTM D 792
Density	1.4	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.05	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.25	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.3	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.08	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+04 – 1.E+07	Ohm	ASTM D 257
INJECTION MOLDING			

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Front - Zone 3 Temperature	380 – 400	°C	
Middle - Zone 2 Temperature	380 – 400	°C	
Rear - Zone 1 Temperature	370 – 380	°C	
Mold Temperature	175 – 190	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	60 – 100	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved