LNP™ STAT-KON™ COMPOUND MFD03

MF-15
REGION ASIA

DESCRIPTION

LNP STAT-KON MFD03 is a compound based on Polypropylene resin containing 15% Glass Fiber. Added features of this material include: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20181220

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	34	MPa	ASTM D 638
Tensile Stress, break	16	MPa	ASTM D 638
Tensile Strain, yield	2.7	%	ASTM D 638
Tensile Strain, break	6.9	%	ASTM D 638
Tensile Modulus, 50 mm/min	3440	MPa	ASTM D 638
Flexural Modulus	2750	MPa	ASTM D 790
Tensile Stress, yield	34	MPa	ISO 527
Tensile Stress, break	15	MPa	ISO 527
Tensile Strain, yield	2.6	%	ISO 527
Tensile Strain, break	5.7	%	ISO 527
Tensile Modulus, 1 mm/min	3310	MPa	ISO 527
Flexural Stress	51	MPa	ISO 178
Flexural Modulus	3000	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	138	J/m	ASTM D 4812
Izod Impact, notched, 23°C	347	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	13	J	ASTM D 3763
Multiaxial Impact	5	J	ISO 6603
Izod Impact, unnotched 80*10*4 +23°C	20	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	5	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	147	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	106	°C	ASTM D 648
CTE, -40°C to 40°C, flow	1.04E-04	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	4.68E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	1.05E-04	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	4.7E-05	1/°C	ISO 11359-2
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	145	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	105	°C	ISO 75/Af
PHYSICAL			
Density	1.07	g/cm³	ASTM D 792
Mold Shrinkage, flow, 24 hrs	1	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.9	%	ASTM D 955

© 2018 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, flow, 24 hrs	1	%	ISO 294
Mold Shrinkage, xflow, 24 hrs	0.92	%	ISO 294
Density	1.07	g/cm³	ISO 1183
INJECTION MOLDING			
Drying Temperature	80	°C	
Drying Time	4	hrs	
Melt Temperature	225 – 250	°C	
Front - Zone 3 Temperature	240 – 250	°C	
Middle - Zone 2 Temperature	215 – 225	°C	
Rear - Zone 1 Temperature	195 – 205	°C	
Mold Temperature	30 – 50	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2018 Copyright by SABIC. All rights reserved