LNP™ STAT-KON™ COMPOUND RE007

RC-1007

DESCRIPTION

LNP STAT-KON RE007 is a compound based on PA66 resin containing 35% Carbon Fiber. Added features include: Electrically Conductive.

TYPICAL PROPERTY VALUES

Revision 20191212

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	275	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.7	%	ASTM D 638
Tensile Modulus, 5 mm/min	29920	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	387	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	24300	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	282	MPa	ISO 527
Tensile Strain, break, 5 mm/min	1.7	%	ISO 527
Tensile Modulus, 1 mm/min	30410	MPa	ISO 527
Flexural Stress	391	MPa	ISO 178
Flexural Modulus, 2 mm/min	24610	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	1030	J/m	ASTM D 4812
Izod Impact, notched, 23°C	103	J/m	ASTM D 256
Multiaxial Impact	3	J	ISO 6603
Instrumented Impact Total Energy, 23°C	7	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	62	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	8	kJ/m²	ISO 180/1A
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	263	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	257	°C	ASTM D 648
CTE, -30°C to 30°C, flow	2.4E-05	1/°C	ASTM D 696
CTE, -30°C to 30°C, xflow	3.7E-05	1/°C	ASTM D 696
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	262	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	256	°C	ISO 75/Af
PHYSICAL			
Specific Gravity	1.33	-	ASTM D 792
Density	1.322	g/cm³	ASTM D 792
Moisture Absorption, 50% RH, 24 hrs	0.59	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	0.2 – 0.4	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	0.9 – 1.1	%	ASTM D 955
Moisture Absorption (23°C / 50% RH)	0.92	%	ISO 62
ELECTRICAL			
Surface Resistivity	1.E+02 – 1.E+05	Ohm	ASTM D 257
INJECTION MOLDING			

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Drying Temperature	80	°C	
Drying Time	4	hrs	
Maximum Moisture Content	0.15 – 0.25	%	
Melt Temperature	280 – 305	°C	
Front - Zone 3 Temperature	295 – 305	°C	
Middle - Zone 2 Temperature	280 – 295	°C	
Rear - Zone 1 Temperature	265 – 275	°C	
Mold Temperature	95 – 110	°C	
Back Pressure	0.2 – 0.3	MPa	
Screw Speed	30 – 60	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved