ULTEM™ RESIN 2100R

REGION ASIA

DESCRIPTION

10% Glass fiber filled, standard flow Polyetherimide (Tg 217C) with internal mold release. ECO Conforming, UL94 V0 and 5VA listing.

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Interiors, Bus, Automotive Under the Hood
Building and Construction	Outdoor, Lawn and Landscape, Construction
Consumer	Sport/Leisure, Personal Accessory, Home Appliance, Personal Recreation, Commercial Appliance, Recreational Vehicle
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure
Hydrocarbon and Energy	Wind Energy, Energy Storage
Industrial	Defense, Semiconductors, Textile, Servomotor, Electronic Material Handling, Industrial Material Handling, Composite, Electronic Material
Mass Transportation	Aircraft Interiors, Specialty Vehicles, Rail
Packaging	Rigid Packaging

TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	114	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	115	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	6	%	ASTM D 638
Tensile Modulus, 5 mm/min	4680	MPa	ASTM D 638
Flexural Stress, brk, 2.6 mm/min, 100 mm span	199	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	5170	MPa	ASTM D 790
Hardness, Rockwell M	114	-	ASTM D 785
IMPACT			
Izod Impact, unnotched, 23°C	480	J/m	ASTM D 4812
Izod Impact, notched, 23°C	85	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	507	J/m	ASTM D 256
THERMAL			
Vicat Softening Temp, Rate B/50	223	°C	ASTM D 1525
HDT, 0.45 MPa, 6.4 mm, unannealed	210	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	208	°C	ASTM D 648
CTE, -20°C to 150°C, flow	3.24E-05	1/°C	ASTM E 831
Relative Temp Index, Elec [1]	170	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	170	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	170	°C	UL 746B
PHYSICAL			
Specific Gravity	1.34	-	ASTM D 792
Water Absorption, 24 hours	0.21	%	ASTM D 570

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, equilibrium, 23C	1.2	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.6	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	7.8	g/10 min	ASTM D 1238
ELECTRICAL			
Volume Resistivity	1.E+17	Ohm-cm	ASTM D 257
Dielectric Strength, in oil, 1.6 mm	27.5	kV/mm	ASTM D 149
Relative Permittivity, 1 kHz	3.5	-	ASTM D 150
Dissipation Factor, 1 kHz	0.0014	-	ASTM D 150
Dissipation Factor, 2450 MHz	0.0046	-	ASTM D 150
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E45587-236982	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.38	mm	UL 94
UV-light, water exposure/immersion	F1	-	UL 746C
Oxygen Index (LOI)	47	%	ASTM D 2863
NBS Smoke Density, Flaming, Ds 4 min	1.8	-	ASTM E 662
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved