ULTEM™ RESIN 2410EPR

REGION ASIA

DESCRIPTION

40% Glass fiber filled, high flow Polyetherimide (Tg 217C) with internal mold release for enhanced electroplatability. ECO Conforming, UL94 V0 listing.

INDUSTRY	SUB INDUSTRY
Consumer	Home Appliances
Electrical and Electronics	Electrical Devices and Displays, Electrical Components and Infrastructure
Industrial	Electronic Material Handling, Electronic Material

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	165	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	165	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	1.8	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	1.8	%	ASTM D 638
Tensile Modulus, 5 mm/min	11100	MPa	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	240	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	10650	MPa	ASTM D 790
Tensile Stress, yield, 5 mm/min	170	MPa	ISO 527
Tensile Stress, break, 5 mm/min	170	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	2	%	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	11000	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	220	MPa	ISO 178
Flexural Modulus, 2 mm/min	9500	MPa	ISO 178
Ball Indentation Hardness, H358/30	165	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched, 23°C	410	J/m	ASTM D 4812
Izod Impact, notched, 23°C	82	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	18	J	ASTM D 3763
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	10	kJ/m²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	10	kJ/m²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	30	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	35	kJ/m²	ISO 179/1eU
THERMAL			
Vicat Softening Temp, Rate B/50	223	°C	ASTM D 1525

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
HDT, 0.45 MPa, 3.2 mm, unannealed	212	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	204	°C	ASTM D 648
HDT, 0.45 MPa, 6.4 mm, unannealed	215	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	208	°C	ASTM D 648
CTE, -40°C to 150°C, flow	1.5E-05	1/°C	ASTM E 831
CTE, -40°C to 150°C, xflow	4.5E-05	1/°C	ASTM E 831
Thermal Conductivity	0.3	W/m-°C	ISO 8302
CTE, 23°C to 150°C, flow	1.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	4.5E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	Passes	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	214	°C	ISO 306
Vicat Softening Temp, Rate B/120	215	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	208	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	205	°C	ISO 75/Ae
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	206	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	197	°C	ISO 75/Af
Relative Temp Index, Elec [1]	105	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	105	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.56	-	ASTM D 792
Mold Shrinkage on Tensile Bar, flow	0.2 – 0.4	%	SABIC method
Mold Shrinkage, flow, 3.2 mm	0.2 – 0.4	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.3 – 0.5	%	SABIC method
Melt Flow Rate, 337°C/6.6 kgf	8.9	g/10 min	ASTM D 1238
Density	1.56	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	0.8	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.4	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	11	cm³/10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥1.5	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥0.75	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 4	≥0.4	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥0.4	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E207780-104152645	-	-
UL Recognized, 94V-0 Flame Class Rating	≥0.4	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Temperature	350 – 400	°C	
Nozzle Temperature	345 – 400	°C	
Front - Zone 3 Temperature	345 – 400	°C	
Middle - Zone 2 Temperature	340 – 400	°C	
Rear - Zone 1 Temperature	330 – 400	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved