ULTEM™ RESIN CRS5201

REGION ASIA

DESCRIPTION

20% Glass fiber filled, standard flow Polyetherimide copolymer (Tg 225C) with enhanced chemical resistance to strong acids, bases, aromatics, and ketones. ECO Conforming, UL94 V0 and 5VA listing.

INDUSTRY	SUB INDUSTRY
Automotive	Heavy Truck, Automotive Interiors, Bus, Automotive Under the Hood
Hydrocarbon and Energy	Fossil
Industrial	Defense
Mass Transportation	Aircraft Interiors, Rail

TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	131	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	5	%	ASTM D 638
Tensile Modulus, 5 mm/min	6890	MPa	ASTM D 638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	213	MPa	ASTM D 790
Flexural Modulus, 2.6 mm/min, 100 mm span	6890	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	74	J/m	ASTM D 256
Izod Impact, Reverse Notched, 3.2 mm	480	J/m	ASTM D 256
THERMAL			
HDT, 1.82 MPa, 6.4 mm, unannealed	218	°C	ASTM D 648
Relative Temp Index, Elec [1]	105	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	105	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	105	°C	UL 746B
PHYSICAL			
Specific Gravity	1.42	-	ASTM D 792
Melt Flow Rate, 337°C/6.6 kgf	2.3	g/10 min	ASTM D 1238
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	5	PLC Code	ASTM D 495
FLAME CHARACTERISTICS [1]			
UL Yellow Card Link	E121562-221118	-	-
UL Recognized, 94V-0 Flame Class Rating	≥1.5	mm	UL 94

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Recognized, 94-5VA Flame Class Rating	≥1.5	mm	UL 94
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Drying Time (Cumulative)	24	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	365 – 390	°C	
Nozzle Temperature	360 – 380	°C	
Front - Zone 3 Temperature	365 – 390	°C	
Middle - Zone 2 Temperature	355 – 375	°C	
Rear - Zone 1 Temperature	345 – 365	°C	
Mold Temperature	135 – 165	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved