ULTEM™ RESIN PW2200

REGION EUROPE

DESCRIPTION

20% Glass fiber filled, standard flow Polyetherimide (Tg 217?C). Specific grade-colors are designed and certified for use in Potable Water applications. KTW, WRAS, ACS, NSF-61 and W270 certified. US FDA and European Food Contact approved.

INDUSTRY	SUB INDUSTRY
Building and Construction	Water Management, Construction

TYPICAL PROPERTY VALUES

Revision 20190717

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Taber Abrasion, CS-17, 1 kg	17	mg/1000cy	SABIC method
Tensile Stress, break, 5 mm/min	140	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2	%	ISO 527
Tensile Modulus, 1 mm/min	6800	MPa	ISO 527
Flexural Stress, break, 2 mm/min	210	MPa	ISO 178
Flexural Modulus, 2 mm/min	6500	MPa	ISO 178
Ball Indentation Hardness, H358/30	150	MPa	ISO 2039-1
IMPACT			
Izod Impact, unnotched 80*10*4 +23°C	30	kJ/m²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	30	kJ/m²	ISO 180/1U
Charpy Impact, notched, 23°C	9	kJ/m²	ISO 179/2C
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	35	kJ/m²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	35	kJ/m²	ISO 179/1eU
THERMAL			
Thermal Conductivity	0.28	W/m-°C	ISO 8302
CTE, 23°C to 150°C, flow	2.5E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	6.0E-05	1/°C	ISO 11359-2
Ball Pressure Test, 125°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate A/50	223	°C	ISO 306
Vicat Softening Temp, Rate B/50	212	°C	ISO 306
Vicat Softening Temp, Rate B/120	218	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	210	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	205	°C	ISO 75/Ae
Relative Temp Index, Elec [1]	170	°C	UL 746B
Relative Temp Index, Mech w/impact [1]	170	°C	UL 746B
Relative Temp Index, Mech w/o impact [1]	170	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.3 – 0.5	%	SABIC method
Density	1.42	g/cm³	ISO 1183
Water Absorption, (23°C/sat)	1	%	ISO 62

© 2019 Copyright by SABIC. All rights reserved

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Moisture Absorption (23°C / 50% RH)	0.55	%	ISO 62
Melt Volume Rate, MVR at 360°C/5.0 kg	7	cm³/10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	4	PLC Code	UL 746A
Hot-Wire Ignition (HWI), PLC 1	≥3	mm	UL 746A
Hot-Wire Ignition (HWI), PLC 2	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 3	≥1.5	mm	UL 746A
High Amp Arc Ignition (HAI), PLC 4	≥3	mm	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
Arc Resistance, Tungsten {PLC}	6	PLC Code	ASTM D 495
FLAME CHARACTERISTICS (1)			
UL Yellow Card Link	E121562-221093	-	-
UL Recognized, 94-5VA Flame Class Rating	≥1.9	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	≥0.41	mm	UL 94
Oxygen Index (LOI)	46	%	ISO 4589
INJECTION MOLDING			
Drying Temperature	150	°C	
Drying Time	4 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	370 – 410	°C	
Nozzle Temperature	360 – 410	°C	
Front - Zone 3 Temperature	370 – 420	°C	
Middle - Zone 2 Temperature	360 – 410	°C	
Rear - Zone 1 Temperature	350 – 400	°C	
Hopper Temperature	80 – 120	°C	
Mold Temperature	140 – 180	°C	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.

© 2019 Copyright by SABIC. All rights reserved